1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ.	DEC.	Weight after Melting. OZ.	DEC.	Loss. OZ.	DEC.	Loss per ct.		Gain. OZ.	DEC.	Description of Bullion.
February 9th	299	G. C. Thompson	30	59	29	15	1	44	4	52			Mch. Cases, Jewelry &c.
	300	Do	17	41	15	81	1	96	11	58			Jewelry Mch. Cases
	1	A. Mecht	13	43	12	50		93	7	15			Mch. Cases & Jewelry
	2	G. C. Thompson	10	02	7	34	2	68	26	80			Assig, Base
	3	Pich & Helms	26	86	26	86							U. S. Coin
	4	Wm. H. Lee	86	00	85	97		03		04			Bars
	5	Do	14	79	14	79							Bullions
	6	Do	4	80	4	80							Button
	7	John Sturdy	8	17	8	17							Button
	8	Phillips & Jacobs	37	60	37	60							U. S. Coin
	9	H. H. Sheafer & Co.	26	85	26	85							Do
10th	10	G. C. Thompson	53	93	53	92		01		02			Bar
	1	Do	38	10	27	00	1	10	3	93			Bars
	2	Do	53	27	49	78	3	49	6	58			Assig
	3	Carrow, Bishop & Co.	22	54	14	84	7	70	33	48			Bars, Base
	4	H. H. Sheafer & Co.	10	87	9	85	1	02	9	27			Jewelry, &c, Silver
11th	5	G. C. Thompson	46	08	41	12	4	96	10	78			Jewelry Mch. Cases
	6	Newlin Bros.	5	89	5	89							Bar
	7	Johnson & Lund	7	10	6	89		21	3	00			Dor. & Phillips
12th	8	Drexel & Co.	10	23	10	23							Dor. Coin
	9	Do	12	59	11	69		90	6	92			Acid, Wyoming
	10	A. Loudon Snowden, Supt.	809	30	809	10		20		02			Bars, U.S. D.C. Mint
	1	H. H. Sheafer & Co.	53	66	53	66							U. S. Coin
	2	F. A. Lyon	6	67	6	55		12	1	71			Dor. & U.S. Coin, Jewelry
	3	Ziegler Bros.	4	46	4	12		34	8	50			Acid, N. C.
13th	4	G. C. Thompson	5	04	4	80		24	4	80			Bars, Dor, &c.
14th	5	Bailey, Banks & Biddle	33	02	24	00	9	02	27	33			Bullions, Base
	6	G. C. Thompson	11	99	9	32	2	77	23	08			Button, Base
	7	H. Muhr's Sons	21	75	21	75							Bars
	8	J. Bishop	9	49	9	49							Bars
	9	J. C. White	11	85	11	49		36	3	00			Dor, &c.
			149	391	145	443	39	48	3	10			

Notes of Melter & Refiner.
3/2/80

Wyoming 1
Montana (1) 1
N. Carolina 1
Fine Bullion (1) 8
Baser 4
Jewelry & Cases 5
very base 4
Coin 5
Dust & Plate 2
Total 31

The losses on the two amalgams from Wyoming & N. Carolina, 6.92 %, & 8½ %, are in fair ratio to the localities; the losses on the finer bullion, 0.01 %, is too low, except for fine Gold; on baser bars 4¼ %; on Jewelry &c. & Cases, 8.61 %; — on very base bullion 27.65 %, are all in due proportion to their character. The loss on coin = .00, is too low for 5 deposits

Jas. L. Booth
M & R.

For week ending February 14th 1880
Approximate value, $22,543.66

S. Colby Dunglison
Register.

RG104 E-1 Box 120
of the Mint.

Report of Gold Deposits
melted for week ending
February 14th 1880

RG104 E-1 Box 120

NARA RG104, Entry 1, Box 120

[Abstract:] Report of Gold Deposits melted for week ending February 14, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]